

Starblanc FBB - Technical Specifications															
Basic Weight		g/m²	195±6	205±6	210±6	225±7	245±7	255±8	275±8	290±9	305±9	330±10	345±10	ISO 536	GB/T451.2
CD Deviation			≤6	≤6	≤6	≤7	≤7	≤8	≤8	≤9	≤9	≤10	≤10		
Caliper (+-10)		m	275	310	320	340	390	415	440	460	500	530	555	ISO 534	GB/T451.3
CD Deviation		%	≤3.0												
CD Stiffness		mN.m	≥2.10	≥3.30	≥3.60	≥4.50	≥6.30	≥7.10	≥8.50	≥10.7	≥12.1	≥12.3	≥14.0	ISO2493, Taber 15°	GB/T 22364
Folding	MD		≥15											ISO5626	GB/T 457
	CD														
Moisture		%	6.5±1.0				7.5±1.0			8.0±1.0		8.5±1.0	ISO287	GB/T462	
Internal Bond		J/m²	≥100								≥120			TAPPI T833	GB/T 26203
D65 D65 Brightness	Top	%	95.0±3.0											ISO2740	GB/T7974
	Back														
Gloss (Top)			≥40											ISO8254	GB/T8941
Smoothness (Top)		s	≥100											ISO5627	GB/T456
PPS (Top)		m	≤1.5											ISO8791-4	GB/T 22363
		%	3-14											-	GB/T 12911
Top		m/s	≥1.20											ISO 3783	GB/T 22365
Cobb, 60s	Top	g/m²	≤45.0											ISO535	GB/T1540
	Back														
Dirt	(0.2-1.0)mm²	m²	≤20											TAPPI T437	GB/T 1541
	(1.0-1.5)mm²														
	>1.5mm²														

